



HARD SURFACE PROTECTION FILM

The below information relates only to the Standard Hard Surface Protection Film.

Description:

Ockwells Hard Surface Protection Film is a 50-micron polythene surface protection film coated with a low tack solvent acrylic adhesive system. Good resistance to moisture, sunlight, and variable climatic conditions. This film is UV stable for up to 6 months.

Applications:

This product can be used on mirror finished steels where bending or cutting is required, as well as to protect medium gloss paint finishes, most non-porous surfaces, hard lacquered finished timber and anodised aluminium laminates. We do not recommend that this product is used on any coated glass (such as Pilkington Suncool™ or other solar control products).

Technical Details

Total thickness: **0.049mm**
Backing thickness: **0.045mm**
Tensile strength: **7n/cm**
Elongation: **150%**
Steel adhesion: **150g/25mm**
Colours: **Blue 600mm wide**

Hard Surface Protection Film can be left in place on internal glass/non-porous surfaces for up to 6 months. It can also be used externally on glass for up to 6 months. The product has been tested without adverse effect on these surfaces. However, due to varying conditions on site and when used in direct sunlight we highly recommend that these time frames are not exceeded. Regular checks should be carried out on the performance of the film to assess if it needs to be removed and replaced.

If this product is used to protect horizontal surfaces any liquid spillages should be removed immediately, and the film should be replaced as this could cause a slip hazard.

This product has been certified as “low slip risk” in dry conditions on hard surfaces but users must satisfy themselves that the product is suitable for the intended purpose.

The company reserves the right to improve products, and any change in specification will result in a re-issue of the information sheet. Please check that you have the latest issue of the information sheet.

Issue Date – October 2023

These properties are the Manufacturers' typical values based on the average of several tests. As the installation and handling of this product is beyond our control the user must ensure that the product is suitable for the application. Ockwells cannot accept responsibility for any loss or damage that may occur either directly or indirectly using this product. Ockwells also holds the right to change specification data without prior notice

NEWBURY

01635 876336
sales@ockwells.co.uk

WARRINGTON

01925 820003
sales.warrington@ockwells.co.uk

GLASGOW

0141 427 3366
sales.glasgow@ockwells.co.uk

EAST LONDON

020 7473 8770
sales.eastlondon@ockwells.co.uk